## (19) World Intellectual Property Organization International Bureau



### 

## (43) International Publication Date 23 January 2003 (23.01.2003)

#### **PCT**

# (10) International Publication Number WO 03/007386 A1

- (51) International Patent Classification<sup>7</sup>: H01L 31/0336, 31/0392
- (21) International Application Number: PCT/US01/22192
- (22) International Filing Date: 13 July 2001 (13.07.2001)
- (25) Filing Language:

English

(26) Publication Language:

English

- (71) Applicant (for all designated States except US): MID-WEST RESEARCH INSTITUTE [US/US]; 425 Volker Boulevard, Kansas City, MO 64110 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): TUTTLE, John, R. [US/US]; 216 A. Fifth Street, Frisco, CO 80446 (US). NOUFI, Rommel [US/US]; 237 Lamb Lane, Golden, CO 80401 (US). HASOON, Falah, S. [IQ/US]; 6416 Simms Street, #43, Arvada, CO 80004 (US).
- (74) Agents: WHITE, Paul, J. et al.; National Renewable Energy Laboratory, 1617 Cole Boulevard, Golden, CO 80401 (US)

- 81) Designated States (national): AE, AG, AL, AM, AT (utility model), AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (utility model), DE, DK (utility model), DK, DM, DZ, EE, ES, FI (utility model), FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

#### Declarations under Rule 4.17:


- of inventorship (Rule 4.17(iv)) for US only
- of inventorship (Rule 4.17(iv)) for US only
- of inventorship (Rule 4.17(iv)) for US only

#### Published:

with international search report

[Continued on next page]

#### (54) Title: THIN-FILM SOLAR CELL FABRICATED ON A FLEXIBLE METALLIC SUBSTRATE



(57) Abstract: A thin-film solar cell (10) is provided. The thin-film solar cell (10) comprises a flexible metallic substrate (12) having a first surface and a second surface. A back metal contact layer (16) is deposited on the first surface of the flexible metallic substrate (12). A semiconductor absorber layer (14) is deposited on the back metal contact. A photoactive film deposited on the semiconductor absorber layer (14) forms a heterojunction structure and a grid contact (24) deposited on the heterjunction structure. The flexible metal substrate (12) can be constructed of either aluminium or stainless steel. Furthermore, a method of constructing a solar cell is provided. The method comprises providing an aluminum substrate (12), depositing a semiconductor absorber layer (14) on the aluminum substrate (12), and insulating the aluminum substrate (12) from the semiconductor absorber layer (14) to inhibit reaction between the aluminum substrate (12) and the semiconductor absorber layer (14).



V 782700/20 OV

# 

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

# THIN-FILM SOLAR CELL FABRICATED ON A FLEXIBLE METALLIC SUBSTRATE

#### Contractual Origin of the Invention

The United States Government has rights in this invention under Contract No. DE-AC36-99GO10337 between the United States Department of Energy and the National Renewable Energy Laboratory, a division of the Midwest Research Institute.

#### 5 Technical Field

This invention relates generally to a thin-film solar cell and, more particularly, to a thin-film solar cell fabricated on a flexible metallic aluminum or stainless steel substrate with appropriate means for inhibiting reaction between the aluminum substrate and the semiconductor absorber.

#### 10 Background Art

15

20

25

Photovoltaic devices, i.e., solar cells, are capable of converting solar radiation into usable electrical energy. The energy conversion occurs as the result of what is known as the photovoltaic effect. Solar radiation impinging on a solar cell and absorbed by an active region of semiconductor material generates electricity.

In recent years, technologies relating to thin-film solar cells have been advanced to realize inexpensive and lightweight solar cells and, therefore, thinner solar cells manufactured with less material have been demanded. This is especially true in the space industry with the solar cells powering satellites and other space vehicles.

The current state of the art in solar cell design is to deposit a photoactive material onto a dense substrate. Typically, the substrate was constructed of glass or a low expansion glass ceramic with densities of approximately 2.2 gms/cc (2200 mg/cc) or higher. Accordingly, the weight of an array or battery of such prior art solar cells is a determining factor in the size of the battery system to be launched into space due to payload weight constraints. Heavy solar cells increase the cost of positioning the satellite into orbit and the operating costs by reducing the payload of the satellite and increasing the launch weight. A lighter weight cell substrate would provide savings in size and weight thereby translating into an increased size for satellite photovoltaic energy systems, which implies higher reliability and accessibility of the satellite throughout its life cycle.

2

Accordingly, there exists a need for a thin-film solar cell fabricated on a flexible metallic substrate which is inexpensive to manufacture. Additionally, a need exists for a thin-film solar cell fabricated on a flexible metallic substrate which is lightweight and reliable for use in space vehicles and other applications. Furthermore, there exists a need for a thin-film solar cell fabricated on a flexible metallic substrate wherein the flexible metallic substrate is an aluminum substrate or a stainless steel substrate with appropriate means between the aluminum substrate and the semiconductor absorber for inhibiting reaction between the aluminum substrate and the semiconductor absorber.

#### **Disclosure of Invention**

10

5

The present invention is a thin-film solar cell comprising a flexible metallic substrate, either aluminum or stainless steel, having a first surface and a second surface. A back metal contact layer is deposited on the first surface of the flexible metallic substrate. A semiconductor absorber layer is deposited on the back metal contact layer. A photoactive film is deposited on the semiconductor absorber layer forming a heterojunction structure. A grid contact is deposited on the heterojunction structure.

15

The present invention additionally includes a solar cell for converting solar radiation into usable electrical energy. The solar cell comprises an aluminum substrate and a semiconductor absorber. Means between the aluminum substrate and the semiconductor absorber inhibit reaction between the aluminum substrate and the semiconductor absorber.

20

The present invention further includes a method of constructing a solar cell. The method comprises providing an aluminum substrate, depositing a semiconductor absorber layer on the aluminum substrate, and insulating the aluminum substrate from the semiconductor absorber layer to inhibit reaction between the aluminum substrate and the semiconductor absorber layer.

#### **Brief Description of Drawings**

25

30

The accompanying drawings, which are incorporated in and form a part of the specification, illustrate the preferred embodiments of the present invention, and together with the descriptions serve to explain the principles of the invention.

#### In the Drawings:

Figure 1 is a sectional view of a thin-film solar cell fabricated on a flexible metallic substrate, constructed in accordance with the present invention;

3

Figure 2 is a sectional view of another embodiment of the thin-film solar cell fabricated on a flexible metallic substrate, constructed in accordance with the present invention;

Figure 3 is a sectional view of still another embodiment of the thin-film solar cell fabricated on a flexible metallic substrate, constructed in accordance with the present invention;

Figure 4 is a sectional view of yet another embodiment of the thin-film solar cell fabricated on a flexible metallic substrate, constructed in accordance with the present invention; and

5

10

15

20

25

30

Figure 5 is a sectional view of still yet another embodiment of the thin-film solar cell fabricated on a flexible metallic substrate, constructed in accordance with the present invention.

Detailed Description of the Preferred Embodiments

As illustrated in Figure 1, the present invention is a thin-film solar cell, indicated generally at 10. The thin-film solar 10 cell has a flexible metallic substrate 12 preferably constructed from an Aluminum (Al) material or a stainless steel material and a semiconductor absorber layer 14 deposited on the flexible metallic substrate 12. The surface of the flexible metallic substrate 12 can be polished (to benefit the film structure of the absorber layer 14 and morphology) or it may be textured (to increase the path length of the reflected light). A chromium adhesion layer, although not always required, can be added to increase adhesion, i.e., a chromium adhesion layer between approximately 100Å and 400Å. Furthermore, the flexible metallic substrate 12 can be thin and flexible, i.e., approximately 25 µm to approximately 100 µm, in order that the thin-film solar cell 10 is lightweight, or the flexible metallic substrate 12 can be thick and rigid to improve handling of the thin-film solar cell 10.

In an embodiment of the present invention, the semiconductor absorber layer 14 is a deposition of high quality Cu(In, Ga)Se<sub>2</sub> (CIGS) thin films providing the fabrication of a high efficiency thin-film solar cell 10. Example processes of deposition of the semiconductor absorber layer 14 are described in U.S. Patent No. 5,436,204 and U.S. Patent No. 5,441,897, which are assigned to the same assignee of the present application and are hereby herein incorporated by reference. It should be noted that the deposition of the CIGS thin film 14 onto the flexible metallic substrate 12 can be by any of a variety of common techniques including, but not limited to, evaporation, sputtering electrodeposition, chemical vapor deposition, etc.

While the deposition of the CIGS thin film 14 has been demonstrated before on other metal foil substrates such as Titanium and Molybdenum, the fundamental hurdle for the

deposition of CIGS thin films 14 onto the Aluminum substrate 12 is that the Aluminum in the Aluminum substrate 12 reacts with the Selenium in the CIGS thin film 14 to form Al<sub>2</sub>Se<sub>3</sub> (an unstable compound in air). Furthermore, at high temperatures, the Aluminum within the Aluminum substrate 12 alloys with the Copper, Indium, and Gallium in the CIGS thin film 14. With the reaction between the Aluminum and the Copper and the alloy of Aluminum with the Copper, Indium, and Gallium, the Aluminum substrate 12 would be essentially consumed during the deposition of the CIGS thin film 14 on the Aluminum substrate 12. A requirement for a properly functioning thin-film solar cell 10 is that the substrate be inert to the film deposited on the substrate.

In order to overcome the consumption of the Aluminum substrate 12 with the CIGS thin film 14 during deposition of the CIGS thin film 14 onto the Aluminum substrate 12, the inventors of the present application discovered that a layer of suitable back metal contact (i.e., conductive metal layer) 16 can be deposited on one or both surfaces of the Aluminum substrate 12 between the Aluminum substrate 12 and the CIGS thin film 14. The back metal contact layer 16 protects and isolates the Aluminum substrate 12 from the fluxes of the Selenium in the CIGS thin film 14 during the deposition of the CIGS thin film 14 onto the Aluminum substrate 12. Preferably, the back metal contact layer 16 is constructed from a Molybdenum (Mo) material. The Molybdenum back metal contact layer 16 preferably has a thickness between approximately 0.1 µm and approximately 1.0 µm although having a Molybdenum back metal contact layer 16 with a thickness less than approximately 0.1 µm and greater than approximately 1.0 µm is within the scope of the present invention. Furthermore, it should be noted that other back metal contact layers 16 besides a Molybdenum back metal contact layer 16 can be used including, but not limited to, a molybdenum/ gold combination, nickel, graphite, etc., (all which have been commonly employed in conventional solar cells).

In addition, as illustrated in Figure 2, when depositing the CIGS thin film 14, a seed layer 18 of In<sub>2</sub>Se<sub>3</sub> or (In,Ga)<sub>2</sub>Se<sub>3</sub> can be deposited on the Molybdenum back metal contact layer 16 which also adds protection of the Aluminum substrate 12 from the CIGS thin film 14. The seed layer 18 of In<sub>2</sub>Se<sub>3</sub> is then followed by the CIGS thin film 16 deposition scheme as described in U.S. Patent No. 5,436,204 and U.S. Patent No. 5,441,897, for instance. While the Molybdenum back metal contact layer 16 is sufficient to protect the Aluminum substrate 12, the In<sub>2</sub>Se<sub>3</sub> seed layer 18 is an added protection at the start of the CIGS thin film 16 deposition, but

5

will end up reacting with the Copper, Indium, Gallium, and Selenium fluxes during the CIGS thin film 14 growth, and is accounted for in the final CIGS thin film 14 composition.

It should be noted that while the CIGS thin film 14 deposition scheme as described in U.S. Patent No. 5,436,204 and U.S. Patent No. 5,441,897 is the preferred deposition of the CIGS thin film 14 onto the Aluminum substrate 12, any other deposition scheme can also be used after the deposition of the Molybdenum back metal contact layer 16 and the In<sub>2</sub>Se<sub>3</sub> seed layer 18.

5

10

15

20

25

30

In a variation of the above-described CIGS thin film 14 deposition scheme, as illustrated in Figures 3, 4, and 5, an insulation layer 20 of SiO<sub>x</sub> and/or Al<sub>2</sub>O<sub>3</sub> (preferred) can be deposited on the Aluminum substrate 12 followed by the Molybdenum back metal contact layer 16. The insulation layer 20 serves as an additional protection for the Aluminum substrate 12 with the Molybdenum back contact layer 16. The primary function, however, of the thin insulation layer 20 is to allow the use of CIGS thin films 14 on the Aluminum substrates 12, in monolithically integrated modules, based on CIGS solar cells. In this configuration, the Aluminum substrate 12 must be electrically isolated from the Molybdenum back metal contact layer 16 in order to accomplish the monolithic interconnect of individual solar cells into a module. In monolithic interconnect CIGS modules, the Aluminum substrate 12 serves as the substrate and the SiO<sub>x</sub> and/or Al<sub>2</sub>O<sub>3</sub> insulation layer 20 serves as an electric isolation between the Aluminum substrate 12 and the Molybdenum back metal contact layer 16. The Molybdenum back contact metal layer is the back contact and the CIGS thin film 14 is the absorber.

Therefore, the thin-film solar cell 10 of the present invention can be constructed in at least the following two variations:

- 1. Al/Mo/CIGS/CdS/ZnO. This structure is for a single, stand-alone thin-film solar cell 10.
- 2. Al/(Al<sub>2</sub>O<sub>3</sub> and/or SiO<sub>x</sub>)/Mo/CIGS/CdS/ZnO)). This structure is necessary for monolithic interconnected modules made up of several thin-film solar cells 10 and can be used for the single, stand-alone thin-film solar cell 10.

In yet another embodiment of the thin-film solar cell 10 of the present invention, the Al<sub>2</sub>O<sub>3</sub> insulation layer 20 can be deposited on the Aluminum substrate 12 by any of a variety of common techniques including, but not limited to, evaporation, sputtering electrodeposition, chemical vapor deposition, etc. In still another embodiment of the thin-film solar cell 10, the Al<sub>2</sub>O<sub>3</sub> insulation layer 20 can be constructed by anodizing the Aluminum substrate 12. The anodization essentially converts the surfaces of the Aluminum substrate 12 to Al<sub>2</sub>O<sub>3</sub> by

6

electrolytic means. It should be noted that in this embodiment, the adhesion layer between the Aluminum substrate 12 and alumina, as described above, is not necessary.

To complete the construction of the thin-film solar cell 10, the CIGS can be paired with a II-VI film 22 to form a photoactive heterojunction. In an embodiment of the present invention, the II-VI film 22 is constructed from Cadmium Sulfide (CdS) although constructing the II-VI films 22 from other materials including, but not limited to, Cadmium Zinc Sulfide (CdZnS), Zinc Selenide (ZnSe), etc., are within the scope of the present invention.

5

10

15

20

25

30

A transparent conducting oxide (TCO) layer 23 for collection of current is applied to the II-VI film. Preferably, the transparent conducting oxide layer 23 is constructed from Zinc Oxide (ZnO) although constructing the transparent conducting oxide layer 23 from other materials is within the scope of the present invention.

A suitable grid contact 24 or other suitable collector is deposited on the upper surface of the TCO layer 23 when forming a stand-alone thin-film solar cell 10. The grid contact 24 can be formed from various materials but should have high electrical conductivity and form a good ohmic contact with the underlying TCO 23. In an embodiment of the present invention, the grid contact 24 is constructed from a metal material, although constructing the grid contact 24 from other materials including, but not limited to, aluminum, indium, chromium, or molybdenum, with an additional conductive metal overlayment, such as copper, silver, nickel, etc., is within the scope of the present invention.

Furthermore, one or more anti-reflective coatings (not shown) can be applied to the grid contact 24 to improve the thin-film solar cell's 10 collection of incident light. As understood by a person skilled in the art, any suitable anti-reflective coating is within the scope of the present invention.

The thin-film solar cell 10 is singular in nature and has variable size, ranging from approximately 1-cm<sup>2</sup> to approximately 100-cm<sup>2</sup> or even larger. In order to series connect singular thin-film solar cells 10, the thin-film solar cells 10 must be separated by cutting or slitting the flexible metallic substrate 12 and then reconnecting the grid contact 24 of one thin-film solar cell 10 to the flexible metallic substrate 12 of another thin-film solar cell 10. In the monolithic integration, the monolithic integrated scheme can be followed to connect the thin-film solar cells 10.

7

The thin-film solar cell 10 of the present invention provides a great advantage over conventional solar cells. The thin-film solar cell 10 with the flexible metallic substrate 12, as described herein, is lighter, less space consuming, and less expensive than using glass or other metallic substrates. Lightness and size are especially useful in space applications where these criteria are important factors. Furthermore, the thin-film solar cell 10 of the present invention can be rolled and/or folded, depending on the desires of the user.

5

10

The foregoing exemplary descriptions and the illustrative preferred embodiments of the present invention have been explained in the drawings and described in detail, with varying modifications and alternative embodiments being taught. While the invention has been so shown, described and illustrated, it should be understood by those skilled in the art that equivalent changes in form and detail may be made therein without departing from the true spirit and scope of the invention, and that the scope of the present invention is to be limited only to the claims except as precluded by the prior art. Moreover, the invention as disclosed herein, may be suitably practiced in the absence of the specific elements which are disclosed herein.

WO 03/007386 . . . PCT/US01/22192

8

#### Claims

The embodiments of the invention in which an exclusive property or privilege is claimed are defined as follows:

1. A thin-film solar cell comprising:

15

20

25

- 5 a flexible metallic substrate having a first surface and a second surface;
  - a back metal contact layer deposited on the first surface of the flexible metallic substrate;
  - a semiconductor absorber layer deposited on the back metal contact;
  - a photoactive film deposited on the semiconductor absorber layer forming a heterojunction structure; and
- a grid contact deposited on the heterojunction structure.
  - 2. The thin-film solar cell of claim 1 wherein the flexible metallic substrate is aluminum.
  - 3. The thin-film solar cell of claim 1 wherein the flexible metallic substrate is stainless steel.
  - 4. The thin-film solar cell of claim 1 wherein the back metal contact is constructed from a Molybdenum (Mo) material.
    - 5. The thin-film solar cell of claim 4 wherein the Molybdenum material has a thickness between approximately 0.1  $\mu$ m and approximately 1.0  $\mu$ m.
    - 6. The thin-film solar cell of claim 1 wherein the semiconductor absorber layer is constructed from a film selected from the group consisting of Cu(In,Ga)Se<sub>2</sub>, CuInSe<sub>2</sub>, CuInSe<sub>2</sub>, CuInSe<sub>2</sub>, and Cu(In,Ga)S<sub>2</sub>.
    - 7. The thin-film solar cell of claim 1 wherein the photoactive film is constructed from Cadmium Sulfide (CdS).
    - The thin-film solar cell of claim 1 and further comprising:
       a transparent conducting oxide for collecting current, the transparent conducting oxide constructed from Zinc Oxide.
    - The thin-film solar cell of claim 1 wherein the grid contact is constructed from metal.
    - 10. The thin-film solar cell of claim 2 and further comprising: an (In,Ga)<sub>2</sub>Se<sub>3</sub> layer deposited between the back metal contact layer and the semiconductor absorber layer.

9

- 11. The thin-film solar cell of claim 2 and further comprising: an Al<sub>2</sub>O<sub>3</sub> layer deposited between the aluminum substrate and the back metal contact layer.
- 12. The thin-film solar cell of claim 11 and further comprising: an insulation layer of SiO<sub>x</sub> deposited on the Al<sub>2</sub>O<sub>3</sub> between the Al<sub>2</sub>O<sub>3</sub> layer and the Molybdenum layer.
  - 13. The thin-film solar cell of claim 2 and further comprising: an insulation layer of SiO<sub>x</sub> deposited between the aluminum substrate and the back metal contact layer.
- 10 14. The thin-film solar cell of claim 2 wherein at least the first surface of the aluminum substrate is anodized thereby forming a layer of Al<sub>2</sub>O<sub>3</sub>.
  - 15. The thin-film solar cell of claim 11 wherein the second surface of the aluminum substrate is anodized.
  - 16. The thin-film solar cell of claim 11 wherein the second surface of the aluminum substrate is protected with SiO<sub>x</sub>.
  - 17. A solar cell for converting solar radiation into usable electrical energy, the solar cell comprising:

an aluminum substrate;

5

15

a semiconductor absorber; and


- 20 means between the aluminum substrate and the semiconductor absorber for inhibiting reaction between the aluminum substrate and the semiconductor absorber.
  - 18. The solar cell of claim 17 wherein the semiconductor absorber is a Cu(In, Ga)Se<sub>2</sub> (CIGS) thin film.
- 19. The solar cell of claim 17 wherein the means between the aluminum substrate and the
   25 semiconductor absorber is a back metal contact layer constructed from a Molybdenum (Mo) material.
  - 20. The solar cell of claim 19 and further comprising:
    an In<sub>2</sub>Se<sub>3</sub> layer deposited between the back metal contact layer and the semiconductor absorber.


10


- 21. The solar cell of claim 19 and further comprising:
  an Al<sub>2</sub>O<sub>3</sub> layer deposited between the aluminum substrate and the back metal contact layer.
- The solar cell of claim 21 and further comprising:
   an insulation layer of SiO<sub>x</sub> deposited on the Al<sub>2</sub>O<sub>3</sub> between the Al<sub>2</sub>O<sub>3</sub> layer and the back contact layer.
  - 23. The solar cell of claim 17 wherein the means between the aluminum substrate and the semiconductor absorber is a layer of Al<sub>2</sub>O<sub>3</sub> anodized from the aluminum substrate.
- 24. A method of constructing a thin-film solar cell, the method comprising:
  providing an aluminum substrate;
  depositing a semiconductor absorber layer on the aluminum substrate; and
  insulating the aluminum substrate from the semiconductor absorber layer to inhibit
  reaction between the aluminum substrate and the semiconductor absorber layer.
- 25. The method of claim 24 herein the semiconductor absorber layer is a Cu(In, Ga)Se<sub>2</sub> (CIGS) thin film.
  - 26. The method of claim 24 wherein the aluminum substrate is insulated from the semiconductor absorber layer by a back metal contact layer constructed from a Molybdenum (Mo) material.
- The method of claim 26 and further comprising:
   depositing an In<sub>2</sub>Se<sub>3</sub> layer between the back metal contact layer and the semiconductor absorber.
  - 28. The method of claim 26 and further comprising:
    depositing an Al<sub>2</sub>O<sub>3</sub> layer between the aluminum substrate and the back metal contact layer.
- 25 29. The method of claim 28 and further comprising: depositing an insulation layer of SiO<sub>x</sub> on the Al<sub>2</sub>O<sub>3</sub> between the Al<sub>2</sub>O<sub>3</sub> layer and the back contact layer.
  - 30. The method of claim 24 and further comprising:
    anodizing a surface of the aluminum substrate; and
    forming a layer of Al<sub>2</sub>O<sub>3</sub> thereby insulating the aluminum substrate from the
    semiconductor absorber layer.


30

1/3










WO 03/007386 . . . PCT/US01/22192

3/3



#### INTERNATIONAL SEARCH REPORT

intermonal Application No PCT/US 01/22192

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01L31/0336 H01L31/0392

According to International Patent Classification (IPC) or to both national classification and IPC

#### B. FIELDS SEARCHED

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, INSPEC, WPI Data

C. DOCUMI	ENTS CONSIDERED TO BE RELEVANT				
Calegory °	Citation of document, with Indication, where appropriate, of t	Relevant to claim No.			
X	EP 0 793 277 A (CANON KK) 3 September 1997 (1997-09-03)	1-4,6-9, 17-19, 24-26			
A	page 2, line 57 -page 19, line 1,2 	11-16, 21-23, 28-30			
X	US 5 141 564 A (CHEN WEN S ET 25 August 1992 (1992-08-25)	1,3,4,6, 7,9			
Y	column 3, line 7 -column 6, li figure 1	2,5,8			
Υ	US 4 536 607 A (WIESMANN HAROL 20 August 1985 (1985-08-20)	2			
A	column 6, line 67 -column 9, 1 figure 2	line 18;	1,3,4,6, 7,9		
<u>.</u>		-/			
X Furti	ner documents are listed in the continuation of box C.	Patent family members are liste	ed in annex.		
'A' docume consid 'E' earlier of filing d 'L' docume which citation 'O' docume other i	int which may throw doubts on priority claim(s) or is clied to establish the publication date of another in or other special reason (as specified) and the referring to an oral disclosure, use, exhibition or	or priority date and not in conflict wi cited to understand the principle or invention  "X" document of particular relevance; the cannot be considered novel or cars involve an inventive step when the "Y" document of particular relevance; the cannot be considered to involve an document is combined with one or ments, such combination being obv in the art.	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled		
Date of the	actual completion of the international search	Date of mailing of the international s	search report		
7	May 2002	15/05/2002			
Name and r	nailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Riiswiik	Authorized officer			

### INTERNATIONAL SEARCH REPORT

Inte mai Application No PC+/US 01/22192

		PC1/US 01/22192				
C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT						
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.				
ſ	US 5 994 163 A (HEDSTROEM JONAS ET AL) 30 November 1999 (1999-11-30)	5,8				
4	column 2, line 12 -column 2, line 36; figure 1	1,4,6,7				
(	US 4 677 250 A (BARNETT ALLEN M ET AL) 30 June 1987 (1987-06-30)	17,18, 21,24, 25,28				
4	column 3, line 60 -column 7, line 19; figures 1-3	1-3,6,7, 9,11-16				
A	NAKADA T ET AL: "SUPERSTRATE-TYPE CUINSE2 THIN FILM SOLAR CELLS WITH SELENIDE BUFFERLAYERS" CONFERENCE RECORD OF THE 25TH. IEEE PHOTOVOLTAIC SPECIALISTS CONFERENCE 1996. WASHINGTON, MAY 13 - 17, 1996, CONFERENCE RECORD OF THE IEEE PHOTOVOLTAIC SPECIALISTS CONFERENCE, NEW YORK, IEEE, US, vol. CONF. 25, 13 May 1996 (1996-05-13), pages 893-896, XP000897003 ISBN: 0-7803-3167-2 figure 2	10,20,27				
A	US 5 441 897 A (NOUFI ROMMEL ET AL) 15 August 1995 (1995-08-15) cited in the application  column 3, line 38 -column 8, line 37; figures 3,5	1,4-6, 10, 17-20, 24-27				

### INTERNATIONAL SEARCH REPORT

in on patent family members

tral al Application No PCT/US 01/22192

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0793277	A	03-09-1997	CN	1174415 A	25-02-1998
			DE	69708463 D1	20-12-2001
			EP	0793277 A2	03-09-1997
			JP	9293892 A	11-11-1997
			KR	267515 B1	16-10-2000
			US 	6072117 A	06-06-2000
US 5141564	A	25-08-1992	NONE		
US 4536607	A	20-08-1985	NONE		
US 5994163	Α	30-11-1999	SE	508676 C2	26-10-1998
			AU	3820595 A	15-05-1996
			EP	0787354 A1	06-08-1997
			JP	10512096 T	17-11-1998
			SE	9403609 A	22-04-1996
			WO	9613063 A1	02-05-1996 
US 4677250	Α	30-06-1987	AU	6448886 A	07-05-1987
			CA	1252874 A1	18-04-1989
•			CA	1262486 A2	24-10-1989
			EP	0221767 A2	13-05-1987
			JP	2025830 C	26-02-1996
			JP	7044288 B	15-05-1995
			JP	62113484 A	25-05-1987
			US	4772564 A	20-09-1988
			US	4781766 A	01-11-1988
US 5441897	Α	15-08-1995	US	5356839 A	18-10-1994
			AU	6628194 A	08-11-1994
			DE	69425255 D1	17-08-2000
			DE	69425255 T2	15-03-2001
			EP	0694209 A1	31-01-1996
			JP	10513606 T	22-12-1998
			JP	3130943 B2	31-01-2001
			JP	8510359 T	29-10-1996
			WO	9424696 A1	27-10-1994
			WO	9625768 A1	22-08-1996
			US	5436204 A	25-07-1995